

Verwey Transition in Magnetite: How fast does an insulator become a metal?

Magnetite (Fe_3O_4), is the first oxide where a relationship between electrical conductivity and fluctuating/localized charges was observed, with a drop in conductivity by two orders of magnitude at $T=123\text{K}$. The Verwey transition is accompanied by a structural change from monoclinic to cubic symmetry. Despite decades of research and indications that charge and orbital ordering play an important role, the mechanism behind the Verwey transition is yet unclear. Recently, three-Fe-site lattice distortions called trimerons have been identified as the true microscopic face of electronic order in low temperature insulating phase. We studied the real time response of insulating magnetite to optical excitation with ultrafast soft X-ray scattering. We discover this to be a two-step process. After an initial femtosecond destruction of individual trimerons in the corresponding lattice, we observe a phase separation into residual insulating trimeron and cubic metallic phases on a 1.5 ± 0.2 picosecond timescale.

Primary author: Ms KUKREJA, Roopali (Stanford University/ SLAC National Accelerator Laboratory)

Co-authors: FÖHLISCH, Alexander (Helmholtz-Zentrum Berlin für Materialien und Energie); Mr BRAUER, Bjorn (SLAC National Accelerator Laboratory); Mr BACK, Christian (Universität Regensburg, Physikalisches Institut); TRABANT, Christoph (II. Physikalisches Institut Universität zu Köln / G-ISRR Helmholtz-Zentrum Berlin); CHANG, Chun Fu (Universität zu Köln, II. Physikalisches Institut); FAUSTI, Daniele (Department of Physics, University of Trieste); ZHU, Dilling (SLAC National Accelerator Laboratory); LU, Donghui (SLAC National Accelerator Laboratory); NOVELLI, Fabio (Department of Physics, University of Trieste); PARMIGIANI, Fulvio (Department of Physics, University of Trieste); DÜRR, Hermann (SLAC National Accelerator Laboratory); TURNER, Joshua J (SLAC National Accelerator Laboratory); PATHEY, Luc (SwissFEL, Paul Scherrer Institut); HOSSAIN, M. A. (SLAC National Accelerator Laboratory); YI, Ming (SLAC National Accelerator Laboratory); Mr BUCHHOLZ, Marcel (Universität zu Köln, II. Physikalisches Institut); TRIGO, Mariano (SLAC National Accelerator Laboratory); Ms DOEHLER, Marita (Universität zu Köln II. Physikalisches Institut); Mr GOLDEN, Mark S. (University Amsterdam, Van der Waals-Zeeman Institute); BEYE, Martin (Helmholtz Zentrum Berlin für Materialien und Energie); Ms ESPOSITO, Martina (Department of Physics, University of Trieste); PONTIUS, Niko (Helmholtz-Zentrum Berlin für Materialien und Energie); Ms SORGENFREI, Nomi (Universität Hamburg, Department of Physics and Center for Free-Electron Laser Science); Mr KRUPIN, Oleg (European XFEL GmbH); Ms METCALF, Patricia (Purdue University, School of Materials Engineering); Dr KIRCHMANN, Patrick (SLAC National Accelerator Laboratory); MOORE, Rob (SLAC National Accelerator Laboratory); KACHEL, Torsten (Helmholtz-Zentrum Berlin für Materialien und Energie); LEE, Wei-Cheng (SLAC National Accelerator Laboratory); Mr WURTH, Wilfried (Universität Hamburg, Department of Physics and Center for Free Electron Laser Science); Mr SCHLOTTER, William F. (SLAC National Accelerator Laboratory); CHUANG, Yi-De (Advanced Light Source)

Presenter: Ms KUKREJA, Roopali (Stanford University/ SLAC National Accelerator Laboratory)

Session Classification: Quantum Materials 2